


# REGANULATE SHEETS WITH COLOURED INCLUSIONS



REGANULATE


PRODUCT NAME AND CODE

Regranulate SCP Select [ R1050 ]

## TECHNICAL SPECIFICATION

COLOUR	BLACK WITH COLOURED INCLUSIONS		
MATERIAL	RUBBER GRANULES SBR, POLYURETHANE BINDER, EPDM RUBBER GRANULES AS AN OPTION		
INCLUSION CONTENT	5%	10%	15%
AREA WEIGHT	1,05 [kg/m2/1mm]		
WIDTH	1 [m]		
MINIMUM DENSITY	1050 [kg/m3]		
FIRE BEHAVIOUR	Efl		
ELECTRICAL RESISTANCE	STATIC DISSIPATIVE		
THERMAL CONDUCTIVITY COEF. $\lambda$	0,17 [W/(mK)]		
THERMAL RESISTANCE R	0,15 [m2 K/W]		
DYNAMIC FRICTION COEFFICIENT	MIN. 0,65 ( $\geq 0,3$ ) KLASA TECHNICZNA DS		
WATERPROOF	THE PRODUCT IS NOT WATERPROOF		

THE TOLERANCE FOR THE GIVEN VALUES IS  $\pm 5\%$  UNLESS IT IS DIFFERENT IN THE CARD



## BRAND

**SCP SELECT**

SCP Ltd

## PRODUCT SPECIFICATION

- SBR rubber reganulate sheet bonded with a polyurethane binder.
- Versatile insulating, damping and anti-slip applications.
- The products meet the requirements of the Ministry of Health and Consumer Protection of 12.03.1996 concerning the content of volatile organic compounds and may be used in rooms of categories A and B intended for human habitation.
- The products are not subject to REACH classification and do not contain substances classified as hazardous.

## STORAGE CONDITIONS

- It is recommended to store the product in warehouse conditions at a temperature of +10 to +25°C.
- Avoid direct sunlight and contact with media that react with rubber: oils, greases, solvents, fuels, acids, etc.
- It is permissible to store the rolls in layers, but not more than four levels.

## COMPLIANCE



## INFORMATION

The information contained in the material data sheet is based on our best knowledge and the results of internal tests. They are indicative and do not constitute a definite guarantee of the properties shown.

The information provided is an indication and cannot be regarded as binding.  
We recommend that you carry out verification tests yourself before using the product.

## DISTRIBUTOR

**SCP**  
Rubber Solutions

SCP Ltd | ul. Turystyczna 1, 43-155 Bieruń | www.scp1.pl