

REGRANULATE SHEETS MIX

PRODUCT NAME AND CODE

Regranulate Mix SCP Select [RM]

TECHNICAL SPECIFICATION

COLOUR	BLACK WITH COLOURED INCLUSIONS	
MATERIAL	RUBBER GRANULATE SBR + POLYURETHANE BINDER + EPDM RUBBER GRANULATE	
AREA WEIGHT	0,75 [kg/m2/1mm]	0,86 [kg/m2/1mm]
WIDTH	1 [m]	
MINIMUM DENSITY	750 [kg/m3]	860 [kg/m3]
TENSILE STRENGTH		650 [kPa]
ELONGATION AT BREAK		55 [%]
FIRE BEHAVIOUR	Efl	
ELECTRICAL RESISTANCE	STATIC DISSIPATIVE	
THERMAL CONDUCTIVITY COEF. λ	0,17 [W/(mK)]	
THERMAL RESISTANCE R	0,15 [m2 K/W]	
DYNAMIC FRICTION COEFFICIENT	MIN. 0,65 ($\geq 0,3$) TECHNICAL CLASS DS	
WATERPROOF	THE PRODUCT IS NOT WATERPROOF	

THE TOLERANCE FOR THE GIVEN VALUES IS $\pm 5\%$ UNLESS IT IS DIFFERENT IN THE CARD

INFORMATION

The information contained in the material data sheet is based on our best knowledge and the results of internal tests. They are indicative and do not constitute a definite guarantee of the properties shown.

The information provided is an indication and cannot be regarded as binding.
We recommend that you carry out verification tests yourself before using the product.



BRAND

SCP SELECT

SCP Ltd

PRODUCT SPECIFICATION

- SBR rubber regranulate sheet bonded with a polyurethane binder.
- Versatile insulating, damping and anti-slip applications.
- The products meet the requirements of the Ministry of Health and Consumer Protection of 12.03.1996 concerning the content of volatile organic compounds and may be used in rooms of categories A and B intended for human habitation.
- The products are not subject to REACH classification and do not contain substances classified as hazardous.

STORAGE CONDITIONS

- It is recommended to store the product in warehouse conditions at a temperature of +10 to +25°C.
- Avoid direct sunlight and contact with media that react with rubber: oils, greases, solvents, fuels, acids, etc.
- It is allowed to store the rolls in layers, but not more than four levels.

COMPLIANCE



DISTRIBUTOR

SCP

Rubber Solutions

SCP Ltd | ul. Turystyczna 1, 43-155 Bieruń | www.scp1.pl