

REGRANULATE RUBBER FLOORINGS

REVOGUM CHECKER

PRODUCT NAME AND CODE

Checker [RGCH]

TECHNICAL SPECIFICATION

PRODUCT FORM	Roll 1,2 x 10 m	
PRODUCT COMPOSITION	RUBBER GRANULES SBR, THERMOPLASTIC POLYMERS	
THICKNESS	3 mm	4 mm
AREA WEIGHT	2,2 [kg/m ²] +/- 10%	2,9 [kg/m ²] +/- 10%
WIDTH	~ 1,2 m	
DENSITY	min. 1 000 [kg/m ³] PN-EN 1602:2013-07	
ELONGATION AT BREAK	63% PN-EN ISO 1798:2009	
TENSILE STRENGTH	3 [N/mm ²] PN-EN ISO 1798:2009	
ABRASION RESISTANCE	237 [mm ³] PN-ISO 4649:2007 (metod A)	
DYNAMIC FRICTION COEFFICIENT μ	0,67 PN-EN 13893:2002	
FIRE BEHAVIOUR	E [PN-EN 13501-1:2019-02]	
TEMPERATURE RESISTANCE	-20°C / 70°C	
LIQUID RESISTANCE	% WEIGHT CHANGE IN OIL IRM 901 - 36% IRM 902 - 70% IRM 903 - 92% PN-ISO 1817:2001	

THE TOLERANCE FOR THE GIVEN VALUES IS \pm 3% UNLESS IT IS DIFFERENT IN THE CARD



BRAND

SCP Ltd

PRODUCT SPECIFICATION

- A recycled product. It is made from finely ground SBR rubber bonded with a thermoplastic polymer.
- It has stabilising and anti-slip properties.
- A product with high mechanical resistance.
- Cushions, dampens and insulates.
- The high degree of compression of the rubber particles, which have been bonded together under heat, translates into a high-density product.
- Can be used outdoors in areas with moderate sun exposure.
- An alternative to SBR vulcanised liners.
- Translated with DeepL.com (free version)

STORAGE CONDITIONS

- The mats should be stored in dry, ventilated rooms, away from heating appliances,
- without direct exposure to the outdoors,
- in such a way as to ensure safe storage and constancy of technical properties.

COMPLIANCE



INFORMATION

The information contained in the material data sheet is based on our best knowledge and the results of internal tests. They are indicative and do not constitute a definite guarantee of the properties shown. The information provided is an indication and cannot be regarded as binding. We recommend that you carry out verification tests yourself before using the product.

DISTRIBUTOR

SCP Ltd | ul. Turystyczna 1, 43-155 Bieruń | www.scp1.pl